

# DATA SHEET

## Cork Underlay

### PRODUCT: R-17 – 2 mm

Size of grains	granulated cork	0,5 / 5 mm
Composition	Raw material – 90%	Binder – 10%
Density	190 kg / m <sup>3</sup> +/- 10kg /m <sup>3</sup>	
Binder	POLYURETANE TDI EXCEPT OF ANY PHTHALATES	
Moisture content	< 7%	<b>EN 12105</b>
Thermal resistance	0,0435 m <sup>2</sup> k/W	
Accoustical properties	17 dB	
Widths possible	1,00 m 1,20 m	1,22 m 1,25 m
Compression	≈ 50 %	
Recovery	≈ 95%	
Thickness	<b>Min. 1,7mm</b>	<b>Max. 2,3mm</b>
Maximum deviation of nominal value	<b>± 0,3mm</b>	<b>ISO 7322:2000</b>
Flexibility	> 5 Kg/cm <sup>2</sup>	
Not torn or open cracks	<b>ISO 4708:2000</b>	Methode A
Fire protection	CLASS: B3	
Tensile strength	<b>Thick ≥ 2 mm ≥ 200 kPa</b>	<b>ISO 7322:2000</b>
Ecological compatibility	Not polluting, not harmful toxicologically	
Quantity / palette	10 m x 1 m x 2 mm	79 rolls
Requirements submitted by:	<b>NP EN 13085:2001</b>	

**Cezar**  
*Perfekcija – krajnjem celu*